

LINTEC TECHNICAL SPECIFICATION

TO (有) アイエムケイ産業

24. APR. 2002

ITEM: PETWH38 (A) MHR 8KX (400500852)

CONSTRUCTION:

PETWH38 (A)	
	MHR
	8KX

FACE MATERIAL ————— POLYESTER FILM, COMPOUNDED OF WHITE PIGMENT

ADHESIVE ————— ACRYLIC TYPE

RELEASE LINER ————— RELEASE COATED GRASINE PAPER

PROPERTIES:

1. PETWH38 (A) FACE MATERIAL

*THICKNESS (μm) 38.0 ± 3.8 (JIS-C-2318)

2. MHR ADHESIVE

*ADHESION SI (mN/25mm) MORE THAN 98 (JIS-Z-0237)

CGS (g/25mm) MORE THAN 10 (JIS-Z-0237)

*HOLDING POWER (SEC) IF OR MORE THAN 10000

3. 8KX RELEASE LINER

*THICKNESS (μm) 67 ± 5 (JIS-P-8118)

*WEIGHT (g/m²) 73.0 ± 4.0, -3.0 (JIS-P-8124)

NOTE: MHR ADHESIVE HOLDING POWER TEST CONDITION

∠0 ° DEAD LOAD TEST AT 40 °C

SPECIMEN 25 mm × 25 mm

DEAD LOAD 9.8 N (1 kgf)

APPLIED TO STAINLESS PLATE

LINTEC CORPORATION
 23-23 HONCHO ITABASHI-KU
 TOKYO 173-0001 JAPAN
 TEL. 03-5248-7727
 FAX. 03-5248-7726

